


IN THE CLAIMS:


Please amend Claims 22 as follows:

22. (Amended) A flame resistant thermoplastic molding composition comprising A) 70 to 98 parts by weight of an aromatic polycarbonate based on one or more of the diphenols of formula (III)



where

A signifies a single bond, C₁-C₆-alkylene, C₂-C₅-alkylidene, C₅-C₆-cycloalkylidene, -S- or -SO₂-, B independently of one another signify C₆-C₁₀-aryl, C₇-C₁₂-aralkyl, q signifies 0, 1 or 2 and p signifies 1 or 0, or of the dihydroxyphenylcycloalkanes of formula (IV),



where

R⁸ and R⁹, independently of one another, signify hydrogen, C₅-C₆-cycloalkyl, C₆-C₁₀-aryl, and C₇-C₁₂-aralkyl, m signifies an integer from 4, 5, 6 or 7, R¹⁰ and R¹¹, are selected individually for each Z and independently of one another, signify hydrogen or C₁-C₆-alkyl and Z signifies carbon, with the proviso that R¹⁰ and R¹¹ both signify alkyl simultaneously on at least one Z atom,

Mo-5383

- 2 -


FAX RECEIVED
JAN 16 2003
GROUP 1700

F1
cont.
Sub
G1

B) 0.5 to 20 parts by weight of a graft polymer having average particle diameter, d_{50} , of 0.05 to 2 μm ,

C) 0.5 to 5 parts by weight of a mixture of

C.1) 10 to 90 wt.%, based on C, of a monophosphorus compound of formula (I)




where

R^1 , R^2 and R^3 , independently of one another, signify C_1 - C_8 -alkyl, C_6 - C_{20} -aryl or C_7 - C_{12} -aralkyl,

m signifies 0 or 1 and n signifies 0 or 1 and

C.2) 90 to 10 wt.%, based on C, of a phosphorus compound of formula (II)



where

R^4 , R^5 , R^6 , R^7 , independently of one another, signify C_1 - C_8 -alkyl, C_5 - C_6 -cycloalkyl, C_6 - C_{10} -aryl or C_7 - C_{12} -aralkyl, l independently of one another, signifies 0 or 1, N signifies 1 to 5 and X signifies a mononuclear or polynuclear aromatic radical with 6 to 30 C atoms and

D) 0.05 to 5 parts by weight of a fluorinated polyolefin with an average particle diameter of 0.05 to 1000 μm , a density of 1.2 to 2.3 g/cm^3 and a fluorine content of 65 to 76 wt.%, and at least one additive selected from the group consisting of stabilizers, dyes, pigments, lubricants, mold release agents, fillers, reinforcing agents, nucleating agents and static agents.